

Preservation Lab - Abbreviated Treatment Report

Database ID 1717 Date received 6/20/2018
Department Classics Library Date Returned 12/19/2018
Item Record # i15549859
Call Number fcl-g AP85.A4
Title Ainos: syngamma periodikon hapax tou mēnos ekdidomenon ..
Author
Imprint

1 In-house Repair 1 Treatment
Performed In-house Repair Catarina Figueirinhas
Staff Type Conservator, Technician, Student T
Time In-house Repair (minutes) 225

2 In-house Repair 2 Treatment
Performed In-house Repair 2 Jessica Ebert
Staff Type Conservator, Technician, Student T
Time In-house Repair 2 10

3 In-house Repair 3 Storage & Handling
Performed In-house Repair 3 Catarina Figueirinhas
Staff Type Conservator, Technician, Student T
Time In-house Repair 3 5

4 Type In-house Repair other
Performed In-house Repair other
Staff Type Conservator, Technician, Student
Time In-house Repair other

Conservator's Note

Treatment was conducted to repair and rebuild the endcaps, consolidate the leather spine, and reinforce the outer and inner joints.

The leather spine was consolidated with Klucel G 3% in isopropanol. The headcap was lined on the inside with toned Usu-Gami Japanese tissue and Zen Shofu wheat starch paste. It was adhered down with Lascaux 489 HV.

The endcap loss was filled with toned Moriki Japanese tissue and wheat starch paste. Several layers of tissue were used to accommodate for the thickness of the spine leather.

The textblock was surface cleaned with an Absorbene sponge. The fly leaf loss was filled with toned Usu-Gami and wheat starch paste. A new flyleaf was hinged with a toned Usu Mino Japanese tissue hinge and

Database ID	1717	Date received	6/20/2018
Department	Classics Library	Date Returned	12/19/2018
Item Record #	i15549859		
Call Number	fcl-g AP85.A4		
Title	Ainos: syngamma periodikon hapax tou mēnos ekdidomenon ..		
Author			
Imprint			

wheat starch paste, in order to protect the title page from the acidity of the pastedown. The inner hinges were reinforced with toned Usu-Gami thinnest tissue hinges and wheat starch paste. The outer hinges were inpainted with Schmincke watercolors and coated with SC6000. The book received a protective polyethylene CoLibri jacket.