

Preservation Lab - Abbreviated Treatment Report

Database ID	2299	Date received	11/5/2019
Department	PLCH	Date Returned	1/9/2020
Item Record #	i104022541		
Call Number	220.074771 qM479Zm 1908		
Title	Daniel B. Meacham Bible collection correspondence scrapbook		
Author	Meacham, Daniel B., compiler		
Imprint	[Cincinnati, Ohio] ; c1908-1947.		

1 In-house Repair 1 Treatment
Performed In-house Repair Ashleigh Schieszer
Staff Type Conservator, Technician, Student C
Time In-house Repair (minutes) 15

2 In-house Repair 2 Treatment
Performed In-house Repair 2 Chris Voynovich
Staff Type Conservator, Technician, Student T
Time In-house Repair 2 60

3 In-house Repair 3 Storage & Handling
Performed In-house Repair 3 Chris Voynovich
Staff Type Conservator, Technician, Student T
Time In-house Repair 3 185

4 Type In-house Repair other
Performed In-house Repair other
Staff Type Conservator, Technician, Student
Time In-house Repair other

Conservator's Note

This is a brown leather 3 ring binder containing dark beige to brown colored leaves with adhered components, including photographs, as well as a pamphlet stuffed into a pocket in the front cover and loose materials of varying formats and sizes placed in the front of the binding.

Treatment:

1. To improve long term storage and handling, polyester film interleaving was added to protect the brittle leaves and attached components, but was not fully encapsulated so that the materials could still be accessible for digitization.

Database ID	2299	Date received	11/5/2019
Department	PLCH	Date Returned	1/9/2020
Item Record #	i104022541		
Call Number	220.074771 qM479Zm 1908		
Title	Daniel B. Meacham Bible collection correspondence scrapbook		
Author	Meacham, Daniel B., compiler		
Imprint	[Cincinnati, Ohio] ; c1908-1947.		

-
2. Loose materials were surface cleaned with an Absorbene soot sponge and tears were repaired with Zen Shofu wheat starch paste. The loose materials were stored in buffered archival folders, outside the binder.
3. Since the binder was showing early signs of red rot, the binder was consolidated overall with 3% Klucel G in isopropanol.
4. Both the foldered objects and the binder were stored together in a corrugated clamshell enclosure.

Scrapbook before treatment